

NEU



XUP - - -.0700

IXI tra-Strong U-Führungsprofil

Werkstoff 25 MnV5mod mit deutlicher höherer Tragfähigkeit.

IXI tra tragfähig
IXI tra genau
IXI tra stark
IXI tra langlebig


- Kammermaßtoleranz 0,2 mm
- Max. Flächenpressung 1060 Mpa
- Streckgrenze ≥ 550 Mpa
- Zugfestigkeit 700 ... 900 Mpa

IXI tra-Strong U guiding profile

Material 25 MnV5mod with plenty more load capacity.

IXI tra sustainable
IXI tra exact
IXI tra strong
IXI tra long-lasting


- Chamber dimension tolerance 0,2 mm
- Max. loading pressure 1060 Mpa
- Elastic limit ≥ 550 Mpa
- Tensile strength 700 ... 900 Mpa



XUP 060.0700

Gewicht/Weight: 9,82 kg/m


Wx: 29,5 cm³
Wy: 11,3 cm³
Ix: 127,9 cm⁴
Iy: 13,8 cm⁴



XUP 070.0700

Gewicht/Weight: 13,97 kg/m


Wx: 50,4 cm³
Wy: 17,6 cm³
Ix: 260,1 cm⁴
Iy: 25,4 cm⁴



XUP 080.0700

Gewicht/Weight: 20,24 kg/m

Wx: 79,0 cm³
Wy: 23,9 cm³
Ix: 479,5 cm⁴
Iy: 35,9 cm⁴



XUP 090.0700

Gewicht/Weight: 27,65 kg/m

Wx: 124,1 cm³
Wy: 43,9 cm³
Ix: 840,2 cm⁴
Iy: 85,2 cm⁴

IXI WALZPROFILE / IXI PROFILES




NEU



XUP 110.0700

Gewicht/Weight: 34,77 kg/m


Wx: 184,6 cm³
 Wy: 65,7 cm³
 Ix: 1451,0 cm⁴
 Iy: 144,2 cm⁴



XUP 120.0700

Gewicht/Weight: 41,69 kg/m


Wx: 242,9 cm³
 Wy: 85,2 cm³
 Ix: 2125,3 cm⁴
 Iy: 197,0 cm⁴



XUP 150.0700

Gewicht/Weight: 50,99 kg/m

Wx: 330,7 cm³
 Wy: 109,7 cm³
 Ix: 3332,3 cm⁴
 Iy: 257,6 cm⁴



XUP ---.0700

IXI tra-Strong

U-Führungsprofil

Werkstoff 25 MnV5mod mit deutlicher höherer Tragfähigkeit.

IXI tra tragfähig

IXI tra genau

IXI tra stark

IXI tra langlebig

- Kammermaßtoleranz 0,2 mm
- Max. Flächenpressung 1060 Mpa
- Streckgrenze ≥ 550 Mpa
- Zugfestigkeit 700 ... 900 Mpa

IXI tra-Strong

U guiding profile

Material 25 MnV5mod with plenty more load capacity.

IXI tra sustainable

IXI tra exact

IXI tra strong

IXI tra long-lasting

- Chamber dimension tolerance 0,2 mm
- Max. loading pressure 1060 Mpa
- Elastic limit ≥ 550 Mpa
- Tensile strength 700 ... 900 Mpa

IXI tra-Strong PROFILE / IXI tra-Strong PROFILES

Sonderbearbeitung auf Anfrage.
Special machining on request.